



Fibrabel® XL



Product class

Not applicable (no class according to EN 622-5)

Scope

High quality ultra lightweight MDF board for non load-bearing applications use in dry conditions.

Description

MDF board with a hard, fine and smoothly sanded surface. MDF Fibrabel® XL has low formaldehyde emission (E1 class). Upon request, this MDF board can be supplied with PEFC, FSC or FSC Controlled Wood certificate.

Use of the product

MDF Fibrabel® XL is suitable for interior decoration, industrial processing and furniture production. The board can be lacquered or finished with paper, foil, veneer or high pressure laminate.

The board must be applied in service class 1 (restrictions in temperature and ambient humidity) and can only be used in biological hazard class 1 of EN 335-3.

The boards must be protected from any direct contact with water. They must be stacked flat, on a pallet or using a sufficient number of cross members. Boards should not be stored vertically, unless ground contact can be avoided. The board will expand or shrink under variable humidity conditions. Use suitable sawing, milling and drilling tools.

Dimensions

Thickness: 25 to 40 mm. Maximum width 220 cm. Maximum length 630 cm. Standard thicknesses and dimensions are listed in our stock program. Furthermore, Spanolux has high capacity saws that support all sawing dimensions. In principle, all thicknesses and lengths/widths are available within the press capabilities.

Contact our sales team or send an e-mail to sales.spanolux@unilin.com for further details.



Fibrabel® XL



Fibrabel® XL

Technical specifications

Property	Test method	Unit	Ranges of nominal thickness (mm)	
			> 19 to 30	> 30 to 45
Swelling in thickness 24 h	EN 317	%	10	10
Internal bond	EN 319	N/mm ²	0,08	0,08
Bending strength	EN 310	N/mm ²	10	8
Modulus of elasticity in bending	EN 310	N/mm ²	1500	1500



Spanolux SPRL - Rue de la Forêt 2 - B-6690 Vielsalm
T +32 80 29 27 10 - F +32 80 29 27 23
sales.spanolux@unilin.com - TVA BE 0456 573 456

The data on this information sheet are based on internal testing and are purely informative and are provided according to Spanolux SPRL knowledge at the time it was issued. Nothing in this information sheet can be construed as a commitment of Spanolux SPRL, nor can it result in any liability whatsoever of Spanolux SPRL. The information provided is subject of change at any time without any prior notification. © Spanolux - all rights reserved

Issue date: 13/06/2016